

Crack Sealing: Field Checklist

Crack sealing field checklist.

Pre-Seal

	TASK	NOTES
■	Cracks blown out with hot air lance / compressor	
■	No moisture in the crack channel	
■	Surface temp 40°F+ and rising	
■	Sealant heated to manufacturer spec (typically 380°F)	
■	Routing depth/width verified where applicable	

Application

	TASK	NOTES
■	Even bead with slight overband	
■	No skips, voids, or thin spots	
■	Detack sand applied where required	
■	Traffic control in place during cure	

Need help executing this plan? Call (406) 309-SEAL or visit summit-surface.com for a free site assessment.